

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : A61L 2/18, 2/20, D21H 21/36	A1	(11) International Publication Number: WO 00/66185 (43) International Publication Date: 9 November 2000 (09.11.00)
--	----	---

(21) International Application Number: PCT/US00/11263

(22) International Filing Date: 27 April 2000 (27.04.00)

(30) Priority Data:
09/302,937 30 April 1999 (30.04.99) US(71)(72) Applicant and Inventor: AAMODT, James [US/US];
4999 Pleasant Ridge Road, The Dallas, OR 97058 (US).

(72) Inventor: COLVIN, John; 1348 N. Locust, Canby, OR 97013 (US).


(74) Agents: BONZAGNI, Mary, R. et al.; Holland & Bonzagni,
P.C., 171 Dwight Road, Longmeadow, MA 01106 (US).

(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published

With international search report.

(54) Title: PAPER PRODUCT IMPREGNATED WITH CHEMICAL MATERIAL



(57) Abstract

The present invention provides a porous paper product impregnated with at least one chemical species. The porous paper product can be in the form of sheets, or compressed pellets. The porous paper can be prepared from a variety of sources, including wood pulp, kenaf, flax, or hemp. The chemical species impregnating the paper react and/or diffuse out of the paper to accomplish a variety of desired results. For example, diffusion of a volatile biocidal chemical out of pores in the paper create a no-growth zone on and immediately surrounding the impregnated paper. In this manner the impregnated paper can provide a sterile environment for activities such as food packaging/storage, the treatment of illness/injury, or waste disposal.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

PAPER PRODUCT IMPREGNATED WITH CHEMICAL MATERIAL

BACKGROUND OF THE INVENTION

1. FIELD OF THE INVENTION

5 The present invention relates to a paper product impregnated with chemical material to accomplish a variety of industrial and household tasks.

2. DESCRIPTION OF THE RELATED ART

10 Paper is typically formed from a mesh of fine fibers, generally of vegetable origin. Currently, wood pulp is the most common source for paper. However, other fibrous material such as cotton, flax, kenaf, hemp, or straw have been used in paper
15 manufacture. Most commonly paper is produced in the form of thin sheets. However paper can also be manufactured in other physical forms such as compressed pellets.

 Paper products currently enjoy widespread use in
20 almost every field of human endeavor. Paper is used as sterile packaging for surgical instruments, and as a cheap, disposable covering for surfaces in treatment and operating rooms. In the food service industry, paper is universally utilized to store both
25 solid and liquid foods, as well as to serve those foods to the consumer. Paper is also emerging as a major component in absorbent material for disposal of wastes from pets and other sources, for example in the material known as cat litter.

Given the wide uses for paper products, there is a need in the art for a paper product which receives, retains, and releases useful chemical species.

Unfortunately, paper provides a suitable
5 environment for the growth of microorganisms. The ability of paper to support the growth of bacteria, molds, or fungi is attributable to the fact that paper is itself derived from living tissue and contains residual organic material that can provide
10 sustenance for microorganisms.

The unwanted growth of microorganisms poses a health hazard for many of the potential applications for paper products. For example, maintaining a sterile environment during the treatment of illness
15 and injury has proven to dramatically reduce the possibility of infection. In the area of food services, maintaining an micro-organism free environment prolongs the viability of foodstuffs, and enhances the effect of such processes as
20 pasteurization. In waste disposal applications, reduction in the growth of microorganisms can cut down on noxious odors and the danger of infection to waste-handlers.

Therefore, there is also a need in the art for a
25 paper product which can inhibit the growth of microorganisms, and which is cheap and easy to manufacture.

SUMMARY OF THE INVENTION

30 The present invention relates to a porous paper
~~material which has been impregnated with at least one~~
chemical material. The impregnating chemical may
beneficially react with other chemicals.

In one embodiment, paper is impregnated with hydrogen peroxide and acetic acid, and reaction between the hydrogen peroxide and acetic acid creates peracetic acid. Peracetic acid is both biocidal and volatile. The gaseous peracetic acid diffuses out of pores in the paper, creating a no-growth zone on the surface of and immediately surrounding the paper. In this manner, chemically impregnated paper in accordance with the present invention may promote a sterile environment useful for a wide variety of activities, for example in the treatment of illness/injury, or in the packaging/storage of foodstuffs.

A method for sterilizing an area in accordance with the present invention comprises the steps of impregnating a porous paper product with a chemical material, placing the porous paper product in the area, and causing reaction of the impregnated chemical material to produce a biocidal compound.

A method for impregnating a porous paper product in accordance with one embodiment of the present invention comprises the steps of providing the porous paper product having pores and a surface, and exposing the surface of the porous paper product to at least one chemical which conveys biocidal properties to the porous paper product.

A composition for producing peracetic acid in accordance with one embodiment of the present invention comprises a porous paper product impregnated with hydrogen peroxide and an acid.

The features and advantages of the present invention will be understood upon consideration of

the following detailed description of the invention and the accompanying drawings.

BRIEF DESCRIPTION OF THE DRAWING

5 FIG. 1 illustrates a method for creating a sterile field utilizing chemically impregnated sheets of paper in accordance with one embodiment of the present invention.

10 DETAILED DESCRIPTION

The present invention relates to a paper product that has been impregnated with at least one chemical. Reaction and/or diffusion of this chemical out of the pores of the paper gives rise to a number of
15 beneficial properties. In particular, diffusion of an impregnating volatile antimicrobial or biocidal agent creates a sterile environment at the surface and in the immediate vicinity of the paper.


Paper is a highly porous material. These pores
20 are defined by space between the extremely fine vegetable fibers making up the mesh. The pores in the paper can receive and contain a wide variety of chemical materials.

For example, the pores in paper can be
25 impregnated with precursors of chlorine dioxide (ClO_2), a gas useful for killing biological contaminants (such as microorganisms, mold, fungi, yeast and bacteria). The biocidal nature of ClO_2 is attributable to its high oxidation potential.

30 Chlorine dioxide can be produced in many ways. For example, it is known to generate chlorine dioxide by adding an acid to a metal chlorite solution. Chlorine dioxide can also be generated by adding

water to a powdered composition such as ferric sulfate or ferric chloride (or other dry composition). An activated dry composition which absorbs water from the air and releases chlorine
5 dioxide over time may also be prepared.

In a first class of embodiments of the present invention, a sheet of paper is successively impregnated with sodium chlorite and acetic acid, or one sheet of paper impregnated with sodium chlorite
10 is placed into contact with another sheet of paper impregnated with acetic acid. Mixing by co-diffusion of the two chemicals causes in the following reaction:



The volatile chlorine dioxide then diffuses from
20 pores of the paper into the surrounding environment. The chlorine dioxide suppresses growth of bacteria, molds, or fungi on the surface of the paper or in areas immediately surrounding the paper.

Acetic acid is only one acid that can generate
25 chlorine dioxide in accordance with the present invention. Sulfuric acid, phosphoric acid, and propionic acid can also react with sodium chlorite to produce chlorine dioxide. Moreover, these acids can also react with paper impregnated with sodium
30 chlorate to produce chlorine dioxide.


FIG. 1 illustrates one embodiment of the present invention, ~~wherein separate sheets of paper 10A and~~
10B are impregnated with sodium chlorite X and acetic

acid Y, respectively. Impregnated papers 10A and 10B are separately stored and transported to the site of use, such as a hospital operating room. At the point of use, impregnated papers 10A and 10B are placed in
5 physical contact. Co-diffusion of the sodium chlorite X and acetic acid Y promotes reaction between these chemicals, forming volatile chlorine dioxide Z. Chlorine dioxide Z outgasses from combined papers 10C, inhibiting the growth of
10 microorganisms on the surface of the combined papers 10C as well as in immediate vicinity 10D of combined papers 10C. This outgassing provides a sterile environment for surgical instrument 12.

In another embodiment of the present invention,
15 a porous paper product in the form of pellets is impregnated with sodium chlorite and acetic acid. Alternatively, a first bed of paper pellets is impregnated with sodium chlorite, and a second bed of paper pellets is impregnated with acetic acid.
20 Mixing together of pellets from the two beds can promote the formation of chlorine dioxide.

In a further alternative embodiment of the present invention, a porous paper product in the form of sheets or pellets is successively impregnated with
25 hydrogen peroxide and an acid. Mixing by co-diffusion of the two impregnating compounds produces a peracid. Acids which may be mixed with hydrogen peroxide to produce the corresponding peracid include but are not limited to: acetic acid; propionic acid;
30 citric acid; benzoic acid; phosphoric acid; lactic acid; butyric acid; pentenoic acid; succinic acid;
~~acid; butyric acid; pentenoic acid; succinic acid;~~
glutaric acid; sorbic acid; and glycolic acid.

The following chemical reaction shows the specific reaction between acetic acid and hydrogen peroxide to produce peracetic acid:



10

Like chlorine dioxide, peracetic acid is a volatile gas having a high oxidation potential and corresponding biocidal properties. Diffusing peracetic acid creates the same type of sterile field discussed above in connection with chlorine dioxide.

A variety of methods may be utilized to impregnate the paper with chemical materials. For example, the paper may be dunked or immersed in a bath containing the chemical, with the liquid chemical drawn into the pores of the paper through the process of diffusion. Alternatively, the chemical may be sprayed upon the surface of the paper, with impregnation of the paper accomplished through diffusion of the chemical from the paper's surface into the underlying pores.

The present invention is applicable to impregnate a variety of porous paper products. Paper made from softwood pulp, kenaf, flax, and hemp are all suitable for chemical impregnation in accordance with the present invention.

In order to further illustrate the present invention, the following experimental examples are described. Each of these examples illustrates

impregnation of paper with chemicals that impart biocidal properties.

Example Number 1

5 The antimicrobial properties of a number of samples of impregnated kenaf papers was determined by exposing *E. coli* bacteria during its growth period to the impregnated paper. This was done by using a zone of inhibition test.

10 A half inch square of the impregnated sample kenaf paper was placed in the center of a Petri dish containing an agar and *E. coli* bacteria spread on the agar surface. Where *E. coli* bacteria were unable to multiply to form visible colonies due to the effects
15 of the test paper, the agar media remained clear. This clear area is known as the zone of inhibition. Bacteria outside of this zone of inhibition are not affected by their proximity to the sample and grow to form visible colonies.

20 A number of samples were prepared according to TABLE 1:

TABLE 1

Sample Number	Sample Components (all % by weight)
5 1	35% aqueous hydrogen peroxide 99% acetic acid
2	paper only - no impregnated chemicals
3	5% d-limonene in water
4	5% d-limonene in water 35% aqueous hydrogen peroxide
5	50% aqueous potassium sorbate 99% acetic acid
10 6	50% aqueous potassium sorbate 5% d-limonene in water
7	50% aqueous potassium sorbate 35% aqueous hydrogen peroxide

The chemicals to be impregnated in each sample were sprayed onto sheets of kenaf paper in equal parts of 2 cc/ft² of paper surface area. The paper was allowed to dry, and a 1/2" x 1/2" square of the impregnated paper was cut to serve as a sample.

A petri dish with Standard Plate Count Agar was inoculated with *E. coli* bacteria by using a bottle with 99 ml sterile phosphate-buffered dilution water, to which is added one loopful of diluted *E. coli* culture. A sterile cotton swab was dipped into the dilution water -containing the *E. coli* culture, then the swab was liberally wiped over the entire surface of the agar. After this, the 1/2 inch square of the paper sample was placed in the middle of the dish, and the dish was then sealed. After two days growth at 35°C, the zone of inhibition around the paper was measured from all four sides and averaged.

The results of the zone of inhibition test for *E. coli* bacteria for the samples listed in TABLE 1 are shown in TABLE 2:

5

TABLE 2
Zone of Inhibition Test Using *E. Coli* Bacteria

	Sample #	Side #1	Side #2	Side #3	Side #4	Avg. Length
	1	2.6 cm	2.7 cm	2.6 cm	2.6 cm	2.63 cm
10	2	0.0 cm	0.0 cm	0.0 cm	0.0 cm	0.0 cm
	3	0.0 cm	0.0 cm	0.0 cm	0.0 cm	0.0 cm
	4	2.9 cm	2.8 cm	3.0 cm	2.7 cm	2.85 cm
	5	1.3 cm	1.0 cm	1.0 cm	1.1 cm	1.1 cm
	6	1.0 cm	1.1 cm	1.0 cm	1.0 cm	1.03 cm
15	7	0.5 cm	0.6 cm	0.5 cm	0.5 cm	0.53 cm

Review of TABLE 2 indicates that sample no. 4 (5% d-limonene/35% aqueous hydrogen peroxide) was most effective in inhibiting the growth of the *E. Coli* bacteria. Sample no. 1 (99% acetic acid/35% aqueous hydrogen peroxide) was the next most effective mixture. Neither the control (sample no. 2) nor d-limonene alone (sample no. 3) showed any effectiveness against the *E. Coli* bacteria.

25

Example Number 2

A second zone of inhibition test was next performed to test the ability of the samples of TABLE 1 to inhibit growth of the *Penicillium* mold.

30

A Petri dish with Standard Plate Count Agar was ~~inoculated with a wild strain of the *Penicillium* mold~~ by using a bottle with 99 ml sterile phosphate-buffered dilution water, to which was added a

moistened cotton swab that has been rubbed on the top of a growing colony of *Penicillium*. A new sterile cotton swab was dipped into the dilution water containing the *Penicillium* culture, then the swab was
5 liberally wiped over the entire surface of the agar. After this, a 1/2 inch square of the paper sample was placed in the middle of the dish, and the dish was then sealed.

After four days growth at room temperature, the
10 zone of inhibition was measured from all four sides and averaged. The results are shown in TABLE 3:

TABLE 3
Zone of Inhibition Test Using
15 Wild Strain of *Penicillium* Mold

Sample #	Side #1	Side #2	Side #3	Side #4	Avg. Length
1	1.8 cm	1.7 cm	1.8 cm	1.9 cm	1.8 cm
2	0.0 cm	0.0 cm	0.0 cm	0.0 cm	0.0 cm
20 3	0.0 cm	0.0 cm	0.0 cm	0.0 cm	0.0 cm
4	2.3 cm	2.2 cm	2.3 cm	2.2 cm	2.25 cm
5	1.1 cm	1.0 cm	1.0 cm	1.0 cm	1.02 cm
6	0.0 cm	0.0 cm	0.0 cm	0.0 cm	0.0 cm
7	0.0 cm	0.0 cm	0.0 cm	0.0 cm	0.0 cm

25 Review of TABLE 3 indicates that sample no. 4 (5% d-limonene/35% aqueous hydrogen peroxide) was again most effective at inhibiting the growth of microorganisms. Sample no. 1 (99% acetic acid/35%
30 aqueous hydrogen peroxide) was again the next most effective mixture. Neither the control (sample no. 2) nor d-limonene alone (sample no. 3) showed any effectiveness against the *Penicillium* mold.

Example Number 3

To evaluate the effect upon biocidal activity of the type of paper impregnated with chemical species, a third zone of inhibition test was conducted. This test utilized a second set of samples prepared according to TABLE 4:

TABLE 4

Sample Number	Paper Type	Sample Components (all % by weight)
8	flax	50% aqueous citric acid 35% aqueous hydrogen peroxide
9	hemp	50% aqueous citric acid 35% aqueous hydrogen peroxide
10	kenaf	50% aqueous citric acid 35% aqueous hydrogen peroxide
11	wood pulp	5% d-limonenein water 35% aqueous hydrogen peroxide
12	kenaf	100% 50% aqueous citric acid
13	kenaf	100% 35% aqueous hydrogen peroxide

Again, the components of each sample were sprayed onto the paper in equal parts of 2 CC/ft² of paper surface area. The paper was allowed to dry, and a 1/2" x 1/2" square of the impregnated paper were then cut to serve as a sample.

A zone of inhibition test was then performed in the presence of *E. coli* bacteria, as otherwise described above in Example Number 1. The results are shown in TABLE 5:

TABLE 5
Zone of Inhibition Test Using *E. Coli* Bacteria

Sample #	Side #1	Side #2	Side #3	Side #4	Avg. Length
8	1.6 cm	1.4 cm	2.0 cm	2.4 cm	1.85 cm
9	1.1 cm	1.6 cm	1.8 cm	1.3 cm	1.45 cm
10	1.9 cm	2.4 cm	2.6 cm	2.7 cm	2.40 cm
11	>3.3 cm	3.0 cm	2.8 cm	2.9 cm	>3.00 cm
12	1.6 cm	1.5 cm	1.4 cm	1.5 cm	1.50 cm
13	2.4 cm	2.9 cm	2.8 cm	2.8 cm	2.73 cm

Review of TABLE 5 indicates that sample no. 11 (50% citric acid/35% aqueous hydrogen peroxide in wood pulp paper) was the most effective at inhibiting the growth of the *E. Coli* bacteria. Sample no. 13 (35% aqueous hydrogen peroxide in kenaf paper) was the next most effective mixture. Hemp paper impregnated with the citric acid/hydrogen peroxide combination evidenced the least biocide activity.

Example Number 4

A zone of inhibition test of the samples of TABLE 4 in the presence of the *Penicillium* mold. The experiment was otherwise conducted in the general manner described above in connection with Example Number 2. The results are shown below in TABLE 6:

TABLE 6
Zone of Inhibition Test Using
Wild Strain of *Penicillium* Mold

5	Sample #	Side #1	Side #2	Side #3	Side #4	Avg. Length
	8	1.9 cm	2.0 cm	2.0 cm	1.8 cm	1.92 cm
	9	2.3 cm	2.0 cm	2.1 cm	1.9 cm	2.07 cm
	10	2.9 cm	2.7 cm	2.8 cm	2.9 cm	2.82 cm
	11	2.6 cm	2.3 cm	2.2 cm	2.4 cm	2.37 cm
10	12	0.0 cm	0.0 cm	0.0 cm	0.0 cm	0.0 cm
	13	1.9 cm	2.0 cm	2.1 cm	1.9 cm	1.97 cm

Review of TABLE 6 indicates that sample no. 9 (50% citric acid/35% aqueous hydrogen peroxide in kenaf paper) was the most effective at inhibiting the growth of the *Penicillium* mold. Sample no. 11 (50% citric acid/35% aqueous hydrogen peroxide in wood paper) was the next most effective combination. Kenaf paper impregnated with citric acid exhibited no biocidal activity.

The impregnated paper product in accordance with the present invention offers a number of important advantages. One advantage is that the paper can be impregnated with the chemical species directly during the paper-making process. For example, before a large sheet of paper is spooled during manufacture, it can be sprayed with a chemical or immersed in a chemical bath. Similarly, paper pellets can be sprayed or immersed in the chemical immediately after assuming their final physical form.

Yet another advantage of chemically-impregnated paper in accordance with the present invention is that its relatively cheap cost facilitates

replacement when the impregnating chemical material becomes spent or exhausted. This is particularly important in medical treatment applications having a low tolerance for contamination, which require frequent replacement of materials in order to maintain the integrity of the sterile field.

Another important advantage of the present invention is its environmental compatibility. Examples 1-4 reveal that impregnated kenaf paper has significant biocidal capability. Kenaf is an annual plant having a paper producing potential approximating that of wood, making it an environmentally-friendly alternative paper source. Moreover, the impregnating chemicals acetic acid, citric acid, and d-limonene are both readily obtained from natural sources. Acetic acid can be obtained by fermentation, citric acid is present in fruits, and d-limonene is derived from orange peels.

Although the invention has been described in connection with specific embodiments, it must be understood that the invention as claimed should not be unduly limited to these embodiments. Various other modifications and alterations in the structure and process will be apparent to those skilled in the art without departing from the scope of the present invention.

For example, while the embodiment of the present invention shown in FIG. 1 describes generating chlorine dioxide from the combination of sodium chlorite and acetic acid, the invention is not limited to these impregnated chemicals. The combination of sodium chlorate and sulfuric acid would also function to generate chlorine dioxide.

This is also true for the combination of either sodium chlorate or sodium chlorite and either ferric chlorate or ferric sulfate.

Moreover, while experimental results have been reported above in conjunction with impregnation of paper with chemicals imparting biocidal activity, paper could be impregnated with a wide variety of other types of chemicals in accordance with the present invention. TABLE 7 provides a partial listing of possible chemicals and chemical combinations suitable for impregnating paper in accordance with the present invention:

TABLE 7

15	IMPREGNATING CHEMICAL SPECIES	PRODUCT CHEMICAL SPECIES	USES FOR PRODUCT CHEMICAL SPECIES
20	1)hydrogen peroxide 2)acid (ex. acetic acid)	peracid	biocide
25	1) sodium chlorite/ sodium chlorate 2)acid (ex. acetic acid)/or metal salt (ex. ferric sulfate)	chlorine dioxide	biocide
	phosphoric acid	$(\text{NH}_4)_2\text{HPO}_4$	odor control (absorption of ammonia)
30	1) permanganate (ex. potassium permanganate) 2) quarternary ammonium cation (ex. cetyltrimethylammonium)	$\text{CO}_2 + \text{H}_2\text{O}$	oxidation and removal of organic contaminants from a mixture
	potassium hydroxide	$\text{KClO}_2 + \text{KClO}_4$	removal of ClO_2
35	sodium sulfite/or sodium bisulfite	$\text{S}_2\text{O}_5 = \text{H}^+\text{ClO}_3$	removal of ClO_2
	manganese dioxide	---	molecular sieve (filtration)

Examples of the chemicals (or inhibitors of chemicals) usefully impregnated into porous paper products (e.g. sheets of paper or paper pellets) include the following:

- 5 sodium chlorate; sodium chlorite; ferric chloride; ferric sulfate; peracetic acid; percitric acid; phosphoric acid; sulfuric acid; propionic acid; citric acid; acetic acid; hydrogen peroxide; calcium chloride; magnesium sulfate; potassium chloride;
- 10 magnesium chloride; sodium bisulfite; sodium metabisulfite; sodium sulfite; d-limonene; potassium sorbate; potassium hydroxide; amino acids; quarternary ammonium cation (including but not limited to cetyltrimethylammonium chloride); urea;
- 15 free amines; copper sulfate; zinc sulfate; cobalt sulfate; magnesium sulfate; copper chloride; zinc chloride; cobalt chloride; magnesium chloride; manganese sulfate; manganese chloride; manganese dioxide; sodium selenate; permanganates (including
- 20 but not limited to potassium permanganate); chlorine; vitamins; lactic acid; benzoic acid; butyric acid; pentenoic acid; succinic acid; glutaric acid; and glycolic acid.

- Given the-multitude of embodiments described
- 25 above, it is therefore intended that the following claims define the scope of the present invention, and that the compositions and methods within the scope of these claims and their equivalents be covered hereby.

WHAT IS CLAIMED IS:

1. A method for sterilizing an area comprising the steps of:
 - 5 impregnating a porous paper product with a chemical material;
 - placing the porous paper product in the area;
 - and
 - causing reaction of the impregnated chemical
 - 10 material to produce a biocidal compound.
 2. The method according to claim 1 wherein the step of impregnating a porous paper product with a chemical material comprises spraying a surface of the
 - 15 porous paper product with the chemical material in liquid form.
 3. The method according to claim 1 wherein the step of impregnating a porous paper product with a
 - 20 chemical material comprises immersing the porous paper product in a bath of the chemical material in liquid form.
 4. The method according to claim 1 wherein the
 - 25 step of impregnating a porous paper product with a chemical material comprises impregnating a sheet of paper.
 5. The method according to claim 1 wherein the
 - 30 step of impregnating a porous paper product with a chemical material comprises impregnating a paper pellet.
-

6. The method according to claim 1 wherein the step of causing reaction of the impregnated chemical material to produce a biocidal compound comprises causing reaction of the impregnated chemical material
5 to produce a volatile biocidal compound in gas form.

7. The method according to claim 6 wherein the step of causing reaction of the impregnated chemical material to produce a volatile biocidal compound
10 comprises causing reaction to produce a peracid.

8. The method according to claim 7 wherein the step of impregnating the porous paper product comprises impregnating the porous paper product with
15 hydrogen peroxide and an acid.

9. The method according to claim 6 wherein the step of impregnating the porous paper product comprises impregnating the porous paper product with
20 hydrogen peroxide and citric acid.

10. The method according to claim 9 wherein the step of impregnating the porous paper product comprises impregnating the porous paper product with
25 equal parts of 50% aqueous citric acid and 35% aqueous hydrogen peroxide.

11. The method according to claim 8 wherein the step of impregnating the porous paper product
30 comprises impregnating the porous paper product with hydrogen peroxide and one of the group composed of
sulfuric acid, acetic acid, phosphoric acid,
potassium sorbate, propionic acid, benzoic acid,

phosphoric acid, lactic acid, butyric acid, pentenoic acid, succinic acid, glutaric acid, and glycolic acid.

5 12. The method according to claim 8 wherein the step of impregnating the porous paper product comprises successively impregnating the porous paper product with equal parts of 99% acetic acid and 35% aqueous hydrogen peroxide.

10

 13. The method according to claim 7 wherein the step of impregnating the porous paper product comprises impregnating the porous paper product with hydrogen peroxide and d-limonene.

15

 14. The method according to claim 13 wherein the step of impregnating the porous paper product comprises impregnating the porous paper product with equal parts of 5% aqueous d-limonene and 35% aqueous
20 hydrogen peroxide.

 15. The method according to claim 7 wherein:
the steps of impregnating the porous paper product comprise impregnating a first porous paper
25 product with hydrogen peroxide and impregnating a second porous paper product with one of d-limonene and an acid; and

the steps of placing the porous paper product in the area and causing reaction comprise placing the
30 first porous paper product in contact with the second porous paper product in the area.

16. The method according to claim 6 wherein the step of causing reaction of the impregnated chemical material to produce a volatile biocidal compound comprises causing reaction to produce chlorine
5 dioxide.

17. The method according to claim 16 wherein:
the step of impregnating the porous paper product comprises impregnating the porous paper
10 product with an acid and at least one of sodium chlorite and sodium chlorate.

18. The method of claim 17, wherein the acid is selected from the group consisting of sulfuric acid,
15 acetic acid, citric acid, phosphoric acid, propionic acid, potassium sorbate, benzoic acid, lactic acid, butyric acid, pentenoic acid, succinic acid, glutaric acid, and glycolic acid.

20 19. The method according to claim 17 wherein:
the step of impregnating the porous paper product comprises impregnating a first porous paper product with an acid and at least one of sodium
chlorite and sodium chlorate.

25 20. The method according to claim 17 wherein:
the step of impregnating the porous paper product comprises impregnating a first porous paper product with an acid and impregnating a second porous
30 paper product with at least one of sodium chlorite
~~and sodium chlorate, and~~

the steps of placing the porous paper product in the area and causing reaction comprise placing the

first porous paper product in contact with the second porous paper product in the area.

21. The method according to claim 16 wherein:
5 the step of impregnating the porous paper product comprises impregnating the porous paper product with a metal salt and at least one of sodium chlorite and sodium chlorate.

10 22. The method according to claim 21, wherein the metal salt is selected from the group consisting of ferric chloride and ferric sulfate.

23. The method according to claim 22 further
15 comprising the step of introducing the metal salt to a moisture containing fluid.

24. The method according to claim 21 wherein the step of impregnating the porous paper product
20 comprises impregnating a first porous paper product with a metal salt and at least one of sodium chlorite and sodium chlorate.

25 25. The method according to claim 21 wherein:
the step of impregnating the porous paper product comprises impregnating a first porous paper product with a metal salt and impregnating a second porous paper with at least one of sodium chlorite and sodium chlorate; and
30 the steps of placing the porous paper product in the area and causing reaction comprise placing the first porous paper product in contact with the second porous paper product in the area.

26. A method for impregnating a porous paper product comprising the steps of:

providing the porous paper product having pores and a surface; and

5 exposing the surface of the porous paper product to at least one chemical which conveys odor controlling properties to the porous paper product.

27. The method according to claim 26 wherein
10 the step of exposing the surface of the porous paper product to a chemical comprises exposing the surface to phosphoric acid.

28. The method according to claim 26 wherein
15 the step of exposing the porous paper product to the chemical comprises spraying the surface of the porous paper product with phosphoric acid.

29. The method according to claim 26 wherein
20 the step of exposing the porous paper product to the chemical comprises immersing the porous paper product in a bath of phosphoric acid.

30. The method according to claim 26 wherein
25 the step of providing a porous paper product comprises providing a sheet of paper formed from at least one of wood pulp, kenaf, flax, and hemp.

31. The method according to claim 26 wherein
30 the step of providing a porous paper product
~~comprises providing a paper pellet formed from at~~
least one of wood pulp, kenaf, flax, and hemp.

32. A method for impregnating a porous paper product comprising the steps of:

providing the porous paper product having pores and a surface; and

5 exposing the surface of the porous paper product to at least one chemical which conveys biocidal properties to the porous paper product.

33. The method according to claim 32 wherein
10 the step of exposing the surface of the porous paper product to the at least one chemical comprises exposing the surface to hydrogen peroxide and an acid.

15 34. The method according to claim 32 wherein the step of exposing the surface of the porous paper product to at least one chemical comprises exposing the surface to hydrogen peroxide and d-limonene.

20 35. The method according to claim 32 wherein the step of exposing the porous paper product to at least one chemical comprises exposing the surface of the porous paper product to at least one of a metal salt and an acid and exposing the surface of the
25 porous paper product to at least one of sodium chlorate and sodium chlorite.

36. The method according to claim 32 wherein the step of exposing the porous paper product to the
30 at least one chemical comprises spraying the porous paper product with the at least one chemical.

37. The method according to claim 32 wherein the step of exposing the porous paper product to the chemical comprises immersing the porous paper product in a bath of the at least one chemical.

5

38. The method according to claim 32 wherein the step of providing a porous paper product comprises providing a sheet of paper formed from at least one of wood pulp, kenaf, flax, and hemp.

10

39. The method according to claim 32 wherein the step of providing a porous paper product comprises providing a paper pellet formed from at least one of wood pulp, kenaf, flax, and hemp.

15

40. A method for impregnating a porous paper product comprising the steps of:

providing the porous paper product having pores and a surface; and

20 exposing the surface of the porous paper product to at least one chemical which conveys chlorine-dioxide destruction properties to the porous paper product.

25 41. The method according to claim 40 wherein the step of exposing the surface of the porous paper product to at least one chemical comprises exposing the surface to at least one chemical selected from the group consisting of potassium hydroxide, sodium sulfite, and sodium bisulfite.

30

42. The method according to claim 40 wherein the step of exposing the porous paper product to the

at least one chemical comprises spraying the porous paper product with the at least one chemical.

43. The method according to claim 40 wherein
5 the step of exposing the porous paper product to the chemical comprises immersing the porous paper product in a bath of the at least one chemical.

44. The method according to claim 40 wherein
10 the step of providing a porous paper product comprises providing a sheet of paper formed from at least one of wood pulp, kenaf, flax, and hemp.

45. The method according to claim 40 wherein
15 the step of providing a porous paper product comprises providing a paper pellet formed from at least one of wood pulp, kenaf, flax, and hemp.

46. A composition producing chlorine dioxide
20 comprising:
a porous paper product impregnated with an acid and at least one of sodium chlorite and sodium chlorate.

25 47. The composition according to claim 46 wherein the porous paper product comprises a first sheet of paper impregnated with an acid and at least one of sodium chlorite and sodium chlorate.

30 48. The composition according to claim 46 wherein the porous paper product comprises a first sheet of paper impregnated with an acid and a second

sheet of paper impregnated with at least one of sodium chlorite and sodium chlorate.

49. The composition according to claim 46
5 wherein the porous paper product comprises a first paper pellet impregnated with an acid and at least one of sodium chlorite and sodium chlorate.

50. The composition according to claim 46
10 wherein the porous paper product comprises a first paper pellet impregnated with an acid and a second paper pellet impregnated with at least one of ferric sodium chlorite and sodium chlorate.

15 51. The composition according to claim 46 wherein the acid is selected from the group consisting of citric acid, sulfuric acid, acetic acid, propionic acid, phosphoric acid, potassium sorbate, benzoic acid, lactic acid, butyric acid,
20 pentenoic acid, succinic acid, glutaric acid, and glycolic acid.

52. A composition producing chlorine dioxide comprising:
25 a porous paper product impregnated with a metal salt and at least one of sodium chlorite and sodium chlorate.

53. The composition according to claim 52
30 wherein the porous paper product comprises a first sheet of paper impregnated with a metal salt and at least one of sodium chlorite and sodium chlorate.

54. The composition according to claim 52 wherein the porous paper product comprises a first sheet of paper impregnated with a metal salt and a second sheet of paper impregnated with at least one
5 of sodium chlorite and sodium chlorate.

55. The composition according to claim 52 wherein the porous paper product comprises a first paper pellet impregnated with a metal salt and at
10 least one of sodium chlorite and sodium chlorate.

56. The composition according to claim 52 wherein the porous paper product comprises a first paper pellet impregnated with a metal salt and a
15 second paper pellet impregnated with at least one of ferric sodium chlorite and sodium chlorate.

57. The composition according to claim 56 wherein the metal salt is selected from the group
20 consisting of ferric sulfate and ferric chloride.

58. A composition producing a peracid, the composition comprising:

a porous paper product impregnated with hydrogen
25 peroxide and an acid.

59. The composition according to claim 58 wherein the porous paper product comprises a first sheet of paper impregnated with hydrogen peroxide and
30 the acid.

60. The composition according to claim 58 wherein the porous paper product comprises a first

sheet of paper impregnated with hydrogen peroxide and
a second sheet of paper impregnated with the acid.

61. The composition according to claim 58
5 wherein the porous paper product comprises a first
paper pellet impregnated with hydrogen peroxide and
the acid.

62. The composition according to claim 58
10 wherein the porous paper product comprises a first
paper pellet impregnated with hydrogen peroxide and a
second paper pellet impregnated with the acid.

63. The composition according to claim 58
15 wherein the acid is selected from the group
consisting of citric acid, sulfuric acid, acetic
acid, propionic acid, phosphoric acid, potassium
sorbate, benzoic acid, lactic acid, butyric acid,
pentenoic acid, succinic acid, glutaric acid, and
20 glycolic acid.

64. The composition according to claim 58
wherein the acid is 50% aqueous citric acid.

25 65. A composition producing peracetic acid, the
composition comprising:
a porous paper product impregnated with hydrogen
peroxide and d-limonene.

30 66. The composition according to claim 65
wherein the porous paper product comprises a first
sheet of paper impregnated with hydrogen peroxide and
d-limonene.

67. The composition according to claim 65 wherein the porous paper product comprises a first sheet of paper impregnated with hydrogen peroxide and a second sheet of paper impregnated with d-limonene.

5


68. The composition according to claim 65 wherein the porous paper product comprises a first paper pellet impregnated with hydrogen peroxide and d-limonene.

10

69. The composition according to claim 65 wherein the porous paper product comprises a first paper pellet impregnated with hydrogen peroxide and a second paper pellet impregnated with d-limonene.

15

70. The composition according to claim 65 wherein the d-limonene has a concentration of about 5% in water.



INTERNATIONAL SEARCH REPORT

Intern. Application No

PCT/US 00/11263

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 A61L2/18 A61L2/20 D21H21/36

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 A61L D21H

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 631 300 A (WELLINGHOFF STEPHEN T) 20 May 1997 (1997-05-20) column 12, line 64 -column 14, line 59; claims; examples	1-6, 16, 26, 30-32, 35-39
X	FR 2 759 911 A (CHEMOXAL SA) 28 August 1998 (1998-08-28) claims 18,19	32, 33, 36-38, 58, 59
X	WO 98 11776 A (BERNARD TECHNOLOGIES INC) 26 March 1998 (1998-03-26) page 36, line 7 - line 17 -/-	26, 32, 40

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents :

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

Z document member of the same patent family

Date of the actual completion of the international search

13 July 2000

Date of mailing of the international search report

21/07/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Songy, 0

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 00/11263

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>EP 0 423 817 A (SQUIBB BRISTOL MYERS CO) 24 April 1991 (1991-04-24)</p> <p>the whole document</p>	<p>1,6, 16-20, 32,46-51</p>

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 00/11263

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 5631300	A	20-05-1997	US 5360609 A	01-11-1994
			AU 698032 B	22-10-1998
			AU 6160296 A	24-12-1996
			BR 9606416 A	14-10-1997
			CA 2196782 A	12-12-1996
			EP 0774898 A	28-05-1997
			JP 10504844 T	12-05-1998
			NZ 310748 A	27-04-1998
			WO 9639029 A	12-12-1996
			US 6046243 A	04-04-2000
			US 5668185 A	16-09-1997
			US 5650446 A	22-07-1997
			US 5980826 A	09-11-1999
			AT 185681 T	15-11-1999
			CA 2115484 A	13-08-1994
			DE 69421199 D	25-11-1999
			DE 69421199 T	20-04-2000
			EP 0611163 A	17-08-1994
			ES 2139709 T	16-02-2000
			JP 2837345 B	16-12-1998
			JP 8165207 A	25-06-1996
			PT 611163 T	28-04-2000
			SG 43915 A	14-11-1997
			AT 173377 T	15-12-1998
			CA 2115483 A	13-08-1994
			DE 69414616 D	24-12-1998
			DE 69414616 T	15-04-1999
			EP 0611162 A	17-08-1994
			ES 2126705 T	01-04-1999
			GR 3029414 T	28-05-1999
			JP 2994199 B	27-12-1999
			JP 8081580 A	26-03-1996
			SG 43357 A	17-10-1997
FR 2759911	A	28-08-1998	EP 0971584 A	19-01-2000
			WO 9837762 A	03-09-1998
WO 9811776	A	26-03-1998	AU 718874 B	20-04-2000
			AU 4230797 A	14-04-1998
			EP 0933991 A	11-08-1999
			US 5965264 A	12-10-1999
EP 0423817	A	24-04-1991	US 5126070 A	30-06-1992
			AU 629701 B	08-10-1992
			AU 6470690 A	26-04-1991
			CA 2027713 A	21-04-1991
			JP 3164403 A	16-07-1991
			NZ 235624 A	23-12-1993